

Thermylon Polyamide 66

Drying Conditions: Dry for 3-6 hours at 185-194°F (85-90°C)
Check moisture before proceeding.
Suggested Max Moisture is 0.2%
Optimum moisture 0.04-0.10%

Screw Type: General Purpose or higher compression Nylon Screw design.
Nozzle Tip: Reverse Taper "Nylon Tip"

General Processing Recommendations

Mold Temperature 167-230°F (75-110°C)
Recommended Melt Temperature 518-554°F (270-290°C)

Injection Pressure: 40-80% of available High – if >80% evaluate flow length
Hold Pressure: 50-100% of peak fill
Back Pressure: Low =<500 PSI, but enough to maintain melt uniformity.
Screw RPM: Medium to High
Injection Speed: Medium-Fast

Regrind: Up to 10% may be used if it is free from oil, grease, dirt and shows no signs of degradation. However, since every application is different, it is recommended that the user should apply appropriate judgment for specific application where the material is used for.

Special Notes: The above recommendations are general guidelines. It may be necessary, depending on material processing equipment and application at hand, to deviate from above guidelines for achieving optimal processing state.

DISCLAIMER OF WARRANTY AND LIABILITY.

Notice: Although the information and recommendations set forth herein are presented in good faith and believed to be correct, Asahi Kasei Corporation expressly disclaims any and all representations and warranties as to the completeness and accuracy thereof. Information is supplied upon the express condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. Asahi Kasei warrants only that this product will perform according to the technical specifications provided in the MSDS and other materials provided by it. No other representations or warranties, expressed or implied, whether oral or arising by usage or trade or course of dealing, without limitation, any warranties of fitness or merchantability, shall be given any legal effect by this product or these materials. This product has not been designed, tested, or intended for any use other than that for which it has been contracted for sale. This product is not warranted against injuries or damages of any kind caused by uses for which this product was not designed, tested or intended. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Asahi Kasei Corporation makes no representation or warranty, express or implied, that the use thereof will not infringe any patent.